



RevXL PH Picture Windows

<i>Glass Type</i>	<i>Application</i>	<i>Gas</i>	<i>U Value (Metric)</i>	<i>U-Value (Imperial)</i>	<i>R-Value</i>	<i>Solar Heat Gain</i>	<i>Visible Light</i>	<i>Condensation Resistance</i>	<i>Energy Rating</i>
Triple Pane-High Performance									
Clear/Clear/SHG	High Solar Gain	Argon	1.14	0.20	5.00	0.51	0.60	71	44
SHG/Clear/SHG		Argon	0.91	0.16	6.25	0.47	0.59	78	47
LowE 2/Clear/Clear	High-Level	Argon	1.08	0.19	5.26	0.29	0.52	72	33
LowE 2 /Clear/SHG		Argon	0.85	0.15	6.67	0.29	0.51	79	38

RevXL_PH Tilt/Turn Windows

<i>Glass Type</i>	<i>Application</i>	<i>Gas</i>	<i>U Value (Metric)</i>	<i>U-Value (Imperial)</i>	<i>R-Value</i>	<i>Solar Heat Gain</i>	<i>Visible Light</i>	<i>Condensation Resistance</i>	<i>Energy Rating</i>
Triple Pane-High Performance									
Clear/Clear/SHG	High Solar Gain	Argon	1.08	0.19	5.26	0.44	0.51	70	42
SHG/Clear/SHG		Argon	0.91	0.16	6.25	0.40	0.51	77	43
LowE 2/Clear/Clear	High-Level	Argon	1.02	0.18	5.56	0.25	0.45	72	32
LowE 2 /Clear/SHG		Argon	0.85	0.15	6.67	0.25	0.44	78	35